



Pacific Wood Laminates, Inc.

Engineered Wood Products

LVL Product Data			
Width	Up to 48 in		
Thickness	Up to 9 in		
Length	Up to 24 ft		
Density	38 lb/ft ³		
Moisture Content	5-9%		
Screw Holding, Edge	377 lb		
Screw Holding, Face	384 lb		
Construction	High Stiffness	Standard	Crossbanded
Modulus of Elasticity	2.25 x 10 ⁶ psi	2.0 x 10 ⁶ psi	1.6 x 10 ⁶ psi
Modulus of Rupture	11,200 psi	10,000 psi	8,100 psi
Typically observed averages. Product construction is customer specific.			
Adhesives			
Phenolic, Melamine, and PVA adhesives are exterior classified and essentially waterproof.			
CARB and TSCA Title VI compliant. No added urea-formaldehyde (NAUF).			
Meets LEED v4 Low-emitting materials requirements.			
Forest Stewardship Council®			
FSC® Controlled Wood and FSC® Mix available			

