



## ProFORM MDO MEL

ProFORM MDO MEL is a premium high-resin melamine concrete form MDO, designed to provide a Non-Architectural Matte finish with moderate grain transfer and specifically formulated to be used with higher alkaline concrete mixes. This product is engineered to provide higher MDO performance as compared to ProForm MDO EF, consistent strength and high re-usability pour after pour. ProForm MDO MEL is best utilized in gang and job-built forms.

## Panel Features

<b>Face Veneer:</b>	B grade grain 1 veneer
<b>Back Veneer:</b>	B grade grain 1 veneer
<b>Inner Plies:</b>	C grade Group 1 veneer
<b>Resin:</b>	Phenolic exterior glue
<b>Dimension:</b>	48" X 96"
<b>Thickness:</b>	3/8" thru 1 1/8"
<b>Edge Seal:</b>	Nox-Crete Edge Flex 645
<b>Release Agent:</b>	Nox-Crete Form Coating
<b>Stamp:</b>	PS-1 APA Trademark
<b>Strength Class:</b>	Struc 1



SCS-COC-00686  
The mark of responsible forestry  
©1996 Forest Stewardship Council

## Handling & Storage

During handling, care should be exercised to prevent panel chipping, denting and corner damage. Panels should never be dropped. After each use, panels should be cleaned of any concrete residue using a hardwood wedge and stiff wire brush. Holes should be repaired and re-edge sealed. Forms should be stacked face to face and stored flat in a protected area prior to next use. Panels should be stored out of the direct sunlight to minimize surface checking and panel dry out.

## Panel Performance

- Non-Architectural Matte Finish
- Increased alkaline resistance
- Moderate grain transfer
- Higher re-use performance
- Lower cost per pour
- Abrasion and wear resistant

## Release Agent

For best performance, we recommend that these panels are coated with a chemically reactive Nox-Crete form release agent. Should be applied before the initial use and each subsequent reuse thereafter to the surface of each panel at the recommended rate per SQ. FT as soon as the panels are stripped and cleaned.

## Overlay Features

ProFORM MDO MEL is overlaid with a 46% resin content, medium-density overlay.

<b>Base paper weight:</b>	46# MSF GSM - 215
<b>Core resin weight:</b>	25# MSF GSM - 123
<b>Glue line weight:</b>	13# MSF GSM - 65
<b>TOTAL:</b>	84# MSF GSM - 403

Span Tables													
Face Grain Across Supports							Face Grain Parallel to Supports						
Support Spacing	3/4		17.5mm / 3/4"		5/8		Support Spacing	3/4		17.5mm / 3/4"		5/8	
	L/360	L/270	L/360	L/270	L/360	L/270		L/360	L/270	L/360	L/270	L/360	L/270
4"	5140	5140	4778	4778	4334	4334	4"	4270	4270	3877	3877	3516	3516
8"	1975	1975	1838	1838	1647	1647	8"	1505	1735	1359	1359	1118	1118
12"	1070	1070	890	890	732	732	12"	580	670	497	604	388	497
16"	550	600	427	501	335	412	16"	250	335	213	283	163	218
19.2"	335	420	256	342	198	264	19.2"	180	210	151	189	116	154
24"	175	235	134	179	103	137	24"	90	125	-	103	-	-